

ssb-30

Sidewall Blocks

Shanxi sidewall blocks



simonsen®

		Typical	Guaranteed	Standard Deviation
Apparent Density: <i>ISO 12985</i> kg/m ³ lbs/cu.ft.	1580 98	1560 97	20
Real Density: <i>ISO 21687</i> kg/m ³ lbs/cu.ft.	1950 121	1920 120	30
Open Porosity: <i>ISO 12985</i> %	17.55	18.00	0.45
Total Porosity: %	18.97	18.75	0.22
Electrical Resistivity: <i>ISO 11713</i> 20°C (68°F) μΩm	37.8	40.0	2.2
Compressive Strength: <i>ISO 18515</i> MPa lbs/sq.in.	34.0 4930	32.0 4640	2.0
Flexural Strength: <i>ISO 12986</i> MPa lbs/sq.in.	8 1160	7 1015	1.0
Ash Content: <i>ISO 8005</i> %	3.8	4.0	0.20
Thermal Conductivity: <i>ISO 12987</i> W/mK	12.0	10.8	1.2
Coefficient of Linear Thermal Expansion: <i>ISO 14420</i> 20-200°C 10 ⁻⁶ /k	3.8	4.0	
Sodium Expansion: <i>ISO 15379</i> %	0.6	0.8	0.2

ssb-30 Sidewall Blocks

Raw Materials:			
	Electro-calcined Anthracite..... %	70	-
	Gas-calcined Anthracite %	-	-
	Graphite scraps %	30	-

Dimensional Tolerances:			
	Length mm	± 3	± 3
	Width mm	± 2	± 2
	Thickness mm	± 2	± 2

Max. sizes:			
	Length mm		700
	Width mm		400
	Thickness mm		90-200

HS Tariff Number: 85451900
(Harmonized Commodity Description and Coding System)

Packing: **ssb-30 sidewall** blocks are packed on double-deck pallets with cardboard protection on all 4 sides and top, nylon straps and plastic foil.

All sidewall blocks are produced by the extrusion production method.

Sidewall blocks can be supplied in strict accordance with customer's drawings and specifications.

The values as per this data-sheet are based upon typical, average test results.

No warranty or guarantee is implied on the data which are given in good faith.

simonsen a/s

Møgelvangs Plads 7
DK-7900 Nykøbing Mors
DANMARK



Producer:
Shanxi Jinyang Carbon Co., Ltd.
Lingshi County, Shanxi Province
P.R. of China

**An ISO-9001, ISO-14001:2004 and
OHSAS 18001:1999 certified company**

