

ssc-10 Cathode Blocks

Shanxi Jinyang Graphitic Cathode Blocks



		Typical	Standard Deviation
Apparent Density: <i>ISO 12985.1</i> kg/m ³	1625	35
 lbs/cu.ft.	101	2
Real Density: <i>ISO 21687</i> kg/m ³	2120	40
 lbs/cu.ft.	132	2.5
Open Porosity: <i>ISO 12985.2</i> %	17.1	2.0
Specific Electrical Resistivity: <i>ISO 11713</i> 20°C (68°F) μΩm	19.6	1.4
Compressive Strength: <i>ISO 18515</i> MPa	31.4	3.0
 lbs/sq.in.	4555	435
Flexural Strength: <i>ISO 12986.1</i> MPa	9.7	2.0
 lbs/sq.in.	1405	290
Ash Contents: <i>ISO 8005</i> %	1.0	0.5
Thermal Conductivity: <i>ISO 12987</i> 20-60°C (68-140°F) W/m K	30.0	3.0
Coefficient of Thermal Expansion: <i>ISO 14420</i> 10 ⁻⁶ /k	3.4	0.2
Sodium Expansion: <i>ISO 15379.1</i> %	0.38	0.12
Raw Materials:			
Electro-calcined Anthracite %	-	
Graphite Scraps %	100	
Dimensional Tolerances:	Length	mm	± 2.0
	Width	mm	± 1.5
	Height	mm	± 1.5
Slots for collector bars:	(All directions).....	mm	± 1.0

ssc-10 Graphitic Cathode Blocks

Max. Sizes Cathode Blocks:	Length	mm	3800
	Width	mm	750
	Height.....	mm	750

HS Tariff Number: 85451900
 (Harmonized Commodity Description and Coding System)

Packing: All **cathode blocks** are packed on pallets, wrapped in plastic foil and packed on wooden pallet and in crates reinforced by steel straps according to international standards.



All blocks are produced by the vibration/compaction production method.

Measurements are made parallel to pressing direction.

Blocks can be supplied in strict accordance with customer's drawings and specifications.

The values as per this datasheet are based upon typical test results.

No warranty or guarantee is implied on the data which are given in good faith.

simonsen a/s
 Møgelvangs Plads 7
 DK-7900 Nykøbing Mors
 DANMARK

Producer:
Shanxi Jinyang Carbon Co., Ltd.
 Lingshi County, Shanxi Province
 P.R. of China

**An ISO-9001, ISO-14001:2015 and
 ISO 45001:2018 certified company**

