



msb® AB-60

Light insulating perlite bricks

		Typical Value	Standard Deviation	
Bulk Density: <i>ISO 5016:1997</i> Kg/m ³	600	19	
 Lbs/cu.ft.	37		
Max. Service Temperature: °C	1050		
 °F	1922		
Cold Crushing Strength: <i>ISO 8895:2006</i> Mpa	4.5	0.65	
 lbs/sq.in.	653		
Refractoriness under Load: <i>ISO 1893:2008</i> @ 960°C (1760°F) Load 0.05 MPa %	0.5		
Modulus of Rupture (MOR): <i>ASTM C 93-83</i> Mpa	1.7		
 lbs/sq.in.			
Linear Reheat Shrinkage: <i>ISO 2477:2005</i> 12 H @ 1000°C (1832°F) %	0.5	0.08	
Coefficient of Reversible Thermal Expansion: <i>EN 821-1:1995</i> 20 to 750°C (68 to 1382°F) °K ⁻¹	6.8 x 10 ⁻⁶		
 °F ⁻¹			
Total Porosity: <i>ISO 5017:2013</i> %	76		
Apparent Porosity: <i>ISO 5017:2013</i> %	63		
Thermal Conductivity: <i>ASTM C 182-88:2009</i> W/m K	@ 200°C	0.16		
	@ 400°C	0.18		
	@ 600°C	0.20		

	Btu/(sq.ft.h°F/in)	@ 390°F.....	1.11	
		@ 750°F.....	1.25	
	@ 1110°F.....	1.39		

		Typical Value
Thermal Conductivity:		
ISO 8894-1/EN 993-14	@ 300°C	0.20
W/m K	@ 600°C	0.24
	@ 900°C	0.27
<hr/>		
	@ 570°F.....	1.39
Btu/(sq.ft.h°F/in)	@ 1110°F.....	1.66
	@ 1650°F.....	1.87

Typical Chemical Analysis: XRF	SiO ₂ (Silicon Dioxide)	%	63.4
	Al ₂ O ₃ (Aluminium Oxide)	%	18.0
	TiO ₂ (Titanium Dioxide)	%	0.6
	Fe ₂ O ₃ (Iron Oxide)	%	3.1
	CaO (Calcium Oxide)	%	7.0
	MgO (Magnesium Oxide)	%	1.6
	K ₂ O (Potassium Oxide)	%	3.6
	Na ₂ O (Sodium Oxide)	%	1.2
Loss on Ignition.....	%	1.5	

Max. sizes available:	Length.....	Max. 250 mm
	Width.....	Max. 250 mm
	Thickness.....	50 to 100 mm

Dimensional Tolerances:	Length.....	± 1.0 mm
	Width.....	± 1.0 mm
	Thickness.....	± 1.0 mm
	Warpage	± 1.0 mm

HS Tariff Number: 6902 2091
(Harmonized Commodity Description and Coding System)

Standard Packing: Double-deck, 4-way pallets, cardboard on 4 sides and top, nylon straps and shrink film.

The strength of the brick increases at rising temperature (ceramic bonded).

Further details about specials etc. are available upon request.

Physical and thermal values are based upon regular, average test results.

No warranty or guarantee is implied on the data, which are given in good faith.

For special shapes and bricks above average size, slight variations in the above data may occur.

Independent test reports available upon request.

simonsen a/s

Møgelvangs Plads 7
DK-7900 Nykøbing Mors
DANMARK

Tel: Int. +45 9669 1300
Fax: Int. +45 9669 1301
simonsen@simonsen.eu
WebSite: www.simonsen.eu



Producer:
MOSCONI SRL.
An ISO-9001:2015 certified company
Annico, Cremona
ITALY

