

# ssb-30

## Sidewall Blocks

Shanxi sidewall blocks



simonsen®

		Typical	Guaranteed	Standard Deviation
<b>Apparent Density:</b> <i>ISO 12985</i>	..... kg/m <sup>3</sup>	1580	1560	20
	..... lbs/cu.ft.	98	97	
<b>Real Density:</b> <i>ISO 21687</i>	..... kg/m <sup>3</sup>	1950	1920	30
	..... lbs/cu.ft.	121	120	
<b>Open Porosity:</b> <i>ISO 12985</i>	..... %	17.55	18.00	0.45
<b>Total Porosity:</b>	..... %	18.97	18.75	0.22
<b>Electrical Resistivity:</b> <i>ISO 11713</i> 20°C (68°F)	..... μΩm	37.8	40.0	2.2
<b>Compressive Strength:</b> <i>ISO 18515</i>	..... MPa	34.0	32.0	2.0
	..... lbs/sq.in.	4930	4640	
<b>Flexural Strength:</b> <i>ISO 12986</i>	..... MPa	8	7	1.0
	..... lbs/sq.in.	1160	1015	
<b>Ash Content:</b> <i>ISO 8005</i>	..... %	3.8	4.0	0.20
<b>Thermal Conductivity:</b> <i>ISO 12987</i>	..... W/mK	12.0	10.8	1.2
<b>Coefficient of Linear Thermal Expansion:</b> <i>ISO 14420</i> 20-200°C	..... 10 <sup>-6</sup> /k	3.8	4.0	
<b>Sodium Expansion:</b> <i>ISO 15379</i>	..... %	0.6	0.8	0.2

**ssb-30 Sidewall Blocks**

<b>Raw Materials:</b>			
	Electro-calcined Anthracite..... %	70	-
	Gas-calcined Anthracite ..... %	-	-
	Graphite scraps ..... %	30	-
<hr/>			
<b>Dimensional Tolerances:</b>			
	Length ..... mm	± 3	± 3
	Width ..... mm	± 2	± 2
	Thickness ..... mm	± 2	± 2
<hr/>			
<b>Max. sizes:</b>			
	Length ..... mm		700
	Width ..... mm		400
	Thickness ..... mm		90-200
<hr/>			
<b>HS Tariff Number:</b>			85451900
(Harmonized Commodity Description and Coding System)			
<hr/>			

**Packing:** **ssb-30 sidewall** blocks are packed on double-deck pallets with cardboard protection on all 4 sides and top, nylon straps and plastic foil.

All sidewall blocks are produced by the extrusion production method.

Sidewall blocks can be supplied in strict accordance with customer's drawings and specifications.

The values as per this data sheet are based upon typical, average test results.

No warranty or guarantee is implied on the data which are given in good faith.

**simonsen a/s**

Møgelvangs Plads 7  
 DK-7900 Nykøbing Mors  
 DANMARK  
 Tel: Int.+45 9669 1300  
 Fax: Int.+45 9669 1301  
 simonsen@simonsen.eu  
 WebSite: www.simonsen.eu



Producer:  
**Shanxi Jinyang Carbon Co., Ltd.**  
 Lingshi County, Shanxi Province  
 P.R. of China

**An ISO-9001, ISO-14001:2015 and  
 ISO 45001:2018 certified company**

